

Base Oil SN150

Properties	Unit	Min.	Typical	Max.	Test Method
Kinematic Viscosity @40°C	cSt	—	38	—	ASTM D 445
Kinematic Viscosity @100°C	cSt	4.6	—	5.6	ASTM D 445
Viscosity Index		100	—	—	ASTM D 2270
Flash Point (COC)	°C	190	—	—	ASTM D 92
Pour Point	°C	—	—	-6	ASTM D 97
CCR	%Wt	—	0.06	—	ASTM D 189
Total Acidity	mgKOH/g	—	—	0.05	ASTM D 664
Demulsibility		—	Pass	—	ASTM D 1401
Sulfur Content	%Wt	0.15	—	0.6	ASTM D 1552
Color		—	0.5	1	ASTM D 1500
Density @15°C	kg/m ³	—	875	—	ASTM D 1298
Copper Corrosion, 3 hrs @100°C		—	—	1A	ASTM D 130
Foam	ml	—	Nil	—	ASTM D 892

