

Triethanol Amine 85% (TEA 85%)

Properties	Unit	Specification	Test Method
Purity	%Wt	85.0 MIN	MA – 503
Sp. Gr. @20/20°C		1.122 – 1.130	ASTM D – 891
Water	%Wt	0.20 MAX	ASTM D -1364
MEA	%Wt	0.50 MAX	MA – 503
DEA	%Wt	15 MAX	MA – 503
Color	Pt-Co	50 MAX	ASTM D – 1209

