

*NISOC SPECIFICATION
DRILLING FLUIDS PRODUCT DATA*

O.B.M . F.L.C.

Product Description:

It is natural asphaltic material to perform fluid loss control.
Also aids in suspension of solids and provides stability of oil muds
at high temperatures.It is soluble in gas oil.

Application:

- Filtration control.
- Suspension .

Typical Physical Properties :

<i>TEST No.</i>		<i>1</i>	<i>2</i>	<i>3</i>	<i>4</i>
OIL/WATER	RATIO	60/40	80/20	60/40	80/20
M.W	PCF	64	90	64	90
GASOIL	ML	187.5	181.5	187.5	181.5
OBM.P.EMUL.	ML	10.5	10.5	10.5	10.5
LIME	GR	12	8	12	8
OBM F.L.C	GR	13	10	13	10
S.S.W	ML	140	57	-	-
SAT. CaCl ₂ WATER	ML	-	-	140	57
OBM VISCOSIFIER	GR	0.5	0.5	0.5	0
OBM.S.EMUL.	ML	3.5	3.5	3.5	3.5
L.S.P	GR	-	245	-	238



O.B.M. F.L.C Continue :

ROLLED IN ROLL.OVEN AT 200 & 250 °F FOR 4 HRS FANN VIS. RUN AT 140 °F AND HPHT F.L. AT 180 & 250°F WITH 500 PSI				
REQ.	1	2	3	4
P.V CPS	15	20	15	20
Y.P LB/100FT ²	10	10	10	10
GELS. LB/100FT ²	6/7	4/5	6/7	4/5
E.S VOLTS	250 min	300 min	400 min	450 min
HPHT F.L. ML	3 max	3 max	3 max	3 max
SETELLING	NIL	NIL	NIL	NIL

Recommended Treatment:

Add 5-15 lb/bbl.

Source :

KPA

Packaging :

25 kg Kraft 3 ply sacks with PE liner.

Marked on: *Name of Manufacturer, Batch No. and Production date.*

Safety Handling:

- Use dust mask, goggles and gloves during usage.
- Avoid skin or eyes contact, in case of contact wash with water.
- Keep in sheltered place.

